

## OK Tigrod NiCu-7

Bare nickel based welding rods alloyed with 30% Cu for welding of base materials of the same type. Can also be used to join these alloys to steel. The weld metal has good resistance to flowing seawater and has high strength and toughness over a rather wide temperature range. Has also good resistance to hydrofluoric acid, sulfuric acid, alkalis etc. Can be used for welding of similar types of base materials which are age-hardenable with small additions of Ti and Al.

|   |  |
|---|--|
| <b>Elettrodo filo - Classificazioni</b> | SFA/AWS A5.14: ERNiCu-7<br>EN ISO 18274: S Ni 4060 (NiCu30Mn3Ti) |
| <b>Approvazioni</b>                     | VdTÜV 12661 (MV)   |

*Le approvazioni si basano sulla localizzazione della fabbrica. Contatta ESAB per maggiori informazioni.*

|                     |   |
|---------------------|---|
| <b>Tipo di lega</b> | Alloyed nickel (Ni + 30 % Cu + 2 % Ti + 2 % Fe) |
|---------------------|---|

### Composizione % tipica del filo

| C    | Mn | Si  | Ni | Al   | Cu | Ti | Fe | Nb+Ta |
|------|----|-----|----|------|----|----|----|-------|
| 0.03 | 3  | 0.3 | 64 | 0.03 | 28 | 2  | 2  | < 0.5 |