



OK Autrod 12.22

Copper-coated, unalloyed wire for Submerged Arc Welding. Suitable in combination with most fluxes. Increased Si content and thus especially for neutral fluxes (e.g: OK Flux 10.62) or in order to increase the fluidity of the molten pool. For structural steels, ship buildings steels, pressure vessel steels, fine grained steels, etc.

Elettrodo filo - Classificazioni	SFA/AWS A5.17 : EM12K EN ISO 14171-A : S2Si
Approvazioni	CE EN 13479 DB 52.039.05 VdTUV 12103 NAKS/HAKC 2.0 mm-5.0 mm

Le approvazioni si basano sulla localizzazione della fabbrica. Contatta ESAB per maggiori informazioni.

Typical Wire Composition %

C	Mn	Si
0.09	1.01	0.19